



Determination of declared value of thermal conductivity (λ_D) of *SELECTION* Agribalance® two component open cell, spray applied, semi-rigid polyurethane foam



VTT Expert Services Ltd

Requested by: IsoGreen Industries Ab.

Requested by IsoGreen Industries Ab
BOX 3095
83103
Sweden

Order E-mail on 21.1.2013 from Lena Kershaw

Contact person **VTT Expert Services Oy**
Research Engineer Hannu Hyttinen
Kemistintie 3
P.O. Box 1001, FIN-02044 VTT
Tel. + 358 20 722 4747
E-mail: hannu.hyttinen@vtt.fi

Task **Determination of declared value of thermal conductivity (λ_D) of SEALECTION Agribalance® two component open cell, spray applied, semi-rigid polyurethane foam**

Declared value of thermal conductivity

The calculations of the declared thermal conductivity value were performed according to the standard EN ISO 10456.

For the calculations were used ten test results measured by VTT Expert Services Ltd.

Value $\lambda_{90/90}$ of the thermal conductivity is calculated using formula 1.

$$\lambda_{90/90} = \lambda_{\text{mean value}} + k \times S_{\lambda} \quad (1)$$

where

$\lambda_{90/90}$ is a 90 % fractile with confidence level of 90 % for the thermal conductivity, W/(m·K).

$\lambda_{\text{mean value}}$ is the mean value of the results of the thermal conductivity measurements, W/(m·K).

k is the factor which depends of the number of test results, 10 test results, **k=2.07** (tabulated value).

S_{λ} is the standard deviation of the test results.

S_λ is calculated using formula 2.

$$S_\lambda = \sqrt{\frac{\sum_{i=1}^n (\lambda_i - \lambda_{ka})^2}{n-1}} \quad (2)$$

The mean value, the standard deviation and the $\lambda_{90/90}$ -value of the test results W/(m·K) are presented in table 1

If the test results meet the requirements of the table 2 of the standard EN ISO 10456 (measurements at + 10 °C mean temperature for dried material) the conversion of the data can be omitted.

The λ -declared-value is calculated rounding the $\lambda_{90/90}$ -value to the nearest higher value with accuracy of 0,001 W/(m·K).

Ten test results measured by VTT Expert Services Ltd were used for the calculations. The detailed test results are presented in test report No. VTT-S-03734-13.

Table 1.

The results of the thermal conductivity measurements, mean value and standard deviation of the test results of SEALECTION Agribalance® two component open cell, spray applied, semi-rigid polyurethane foam.

Test specimen / Manufacturing day	Dry density ρ (kg/m ³)	Thermal conductivity λ_{10} W/(m·K)
1	9.2	0.0380
2	9.1	0.0382
3	9.0	0.0373
4	9.0	0.0369
5	9.5	0.0369
6	9.0	0.0375
7	9.6	0.0368
8	8.9	0.0368
9	9.2	0.0375
10	9.5	0.0367
Mean value	9.2	0.03726
Standard deviation S_λ	-	0.000532

Table 2. *The $\lambda_{90/90}$ -value and the declared value of thermal conductivity of SEALECTION Agribalance® two component open cell, spray applied, semi-rigid polyurethane foam.*

Mean value of thermal conductivity λ_{10} W/(m·K)	k-factor (10 test results)	Standard deviation S_{λ}	$\lambda_{90/90}$ -value	Declared value of thermal conductivity λ_D (W/mK)
0.03726	2.07	0.000532	0.03836	0.039

λ -declared values is given according to the standard EN ISO 10456 table 2, set I (10 °C) a.

Espoo 27.5.2013



Hannu Hyttinen
Research Engineer



Paulina Tiainen
Laboratory Technician

DISTRIBUTION

Customer
VTT
Liisa Rautiainen / VTT Expert Services Oy

Original
Original

Copy