

VTT Expert Services Ltd
PL 1001
02044 VTT
Puh. +358 20 722 4911
Telekopio +358 20 722 7003



Rakennustuotedirektiivin (89/106/EEC) artiklan 10,
neuvoston direktiivi 21. joulukuuta 1988,
mukaisesti notifioitu tuotehyväksyntälaitos

EOTAN JÄSEN

Eurooppalainen tekninen hyväksyntä ETA - 13/0613 European Technical Approval

Kauppanimi:

Trade name

Sealection® Agribalance spray foam insulation

Hyväksynnän haltija:

Holder of approval:

IsoGreen Industries AB

p.o. Box 3095
SE-83103 Östersund
Sweden

Tuotetyyppi ja sen käyttötarkoitus:

Generic type and use of construction
product:

Rakennusten lämmön- ja ääneneriste

Thermal and acoustic insulation for building

Voimassaoloaika: Validity from/to

Tämä versio korvaa: This version
replaces:

From June 30, 2013 to June 30, 2018

Valmistuspaikka:

Manufacturing plants:

Demilec (USA) LLC

2925 Galleria Drive
Arlington, TX 76011

Tämä hyväksyntä sisältää

This European Technical Approval
contains

sivuja/liitteitä

pages/annexes

6 sivua, ei liitteitä

6 pages including no annexes



Eurooppalainen tekninen hyväksyntäorganisaatio
European Organisation for Technical Approvals

I LEGAL BASIS AND GENERAL CONDITIONS

1. This European Technical Approval is issued by the VTT Expert Services Ltd in accordance with:
 - Council Directive 89/106/EEC of 21 December 1988 on the approximation of laws, regulations and administrative provisions of Member States relating to construction products¹, modified by the Council Directive 93/68/EEC² and Regulation (EC) N° 1882/2003 of the European Parliament and of the Council³,
 - Laki rakennustuotteiden hyväksynnästä (230/2003) luvut 3 ja 10, Ympäristöministeriön asetus rakennustuotteiden hyväksynnästä 3 § sekä Ympäristöministeriön 18.12.2009 antama valtuutuspäätös (19/629/2009),
 - Common Procedural Rules for Requesting, Preparing and the Granting of European Technical Approvals set out in the Annex of Commission Decision 94/23/EC⁴;
2. The VTT Expert Services Ltd is authorised to check whether the provisions of this European Technical Approval are met. Checking may take place in the manufacturing plant(s). Nevertheless, the responsibility for the conformity of the products to the European Technical Approval and for their fitness for the intended use remains with the holder of the European Technical Approval.
3. This European Technical Approval is not to be transferred to manufacturers or agents of manufacturer other than those indicated on Annex 1; or manufacturing plants other than those indicated on page 1 of this European Technical Approval.
4. This European Technical Approval may be withdrawn by the VTT Expert Services Ltd pursuant to Article 5 (1) of the Council Directive 89/106/EEC.
5. Reproduction of this European Technical Approval including transmission by electronic means shall be in full. However, partial reproduction can be made with the written consent of the VTT Expert Services Ltd. In this case partial reproduction has to be designated as such. Texts and drawings of advertising brochures shall not contradict or misuse the European Technical Approval.
6. The European Technical Approval is issued by VTT Expert Services Ltd in English. This version corresponds to the version circulated within EOTA. Translations into other languages have to be designated as such.

¹ Official Journal of the European Communities N° L 40, 11.2.1989, p. 12

² Official Journal of the European Communities N° L 220, 30.8.1993, p. 1

³ official Journal of the European Union N° L 284, 31.10.2003, p. 25

⁴ Official Journal of European Communities N° L 17, 20.1.1994, p. 34

II SPECIFIC CONDITIONS OF THE EUROPEAN TECHNICAL APPROVAL

1. Definition of the product and intended use

1.1 Definition of the construction product

Sealection Agribalance is two component open cell, spray applied, semi-rigid polyurethane foam. The insulation is sprayed or injected. It is produced by mixing the resin and polyisocyanate components together.

1.2 Intended use

The product is intended to be used inside external or internal walls, partitions, floors, intermediate floors, ceilings and underside of roofs and underside of decks as thermal and acoustical insulation in such constructions where it is not subjected to loads or not exposed to wetting, weathering, heavy moisture transport or heavy condensation.

The provisions made in this ETA are based on an assumed working life of the thermal insulation of 50 years provided that the conditions laid down in this section and sections 4.2/5.1/5.2 for the packaging, transport, storage, installation, use maintenance and repair are met. The indications given on the working life cannot be interpreted as a guarantee given by the producer, but are to be regarded only as a means for choosing the right products in relation to the expected economically reasonable working life of the works.

1. Characteristics of product and methods of verification

The methods of verification and characteristics of the thermal insulation evaluated in this ETA are as follows:

CUAP Paragraph	Characteristic	Assessment of the characteristic
ER1 Mechanical resistance and stability		
2.4.1	Corrosion developing capacity on metal constructions	No pits (perforations) were observed on the copper sheets. Several (15 pcs) pits of Ø 1.0 – 7.0 mm and several smaller (68 pcs) pits and very small (15 pcs) pits were observed on the sheet of zinc, Za1. Several (15 pcs) pits of Ø 1.0 – 7.0 mm and several smaller (40 pcs) pits and very small (30 pcs) pits were observed on the sheet of zinc, Za2.
ER2 Safety in case of fire		
2.4.2	Reaction to fire (insulation)	Class F (not tested)
ER 3 Hygiene, health and environment		
2.4.3	Content and release of dangerous substances	No dangerous substances *) No flame retardants or biocides
2.4.4	Water absorption, EN 1609	2,64 kg/m²
2.4.5	Water vapour permeability, EN 12086 μ-value	3,187 x 10⁻¹¹ kg/msPa 6,11
2.4.6	Susceptibility to mould growth, CUAP Annex B	Rating 0 (without spore addition) Rating 0 (with spore addition) Not relevant
ER 4 Safety in use		
ER 5 Protection against noise		
2.4.7	Dynamic stiffness, EN 29052-1 Compressibility (thickness change), EN 12431	9 MN/m³ (density c. 13,4 kg/m ³) 9,2 % (density _{mean} 12,0 kg/m ³)
ER 6 Energy economy and heat retention		
2.4.8	Thermal conductivity, λ _{90/90, dry at 10 °C} **Thermal conductivity, λ _{DECLARED} , EN 12667 and EN ISO 10456	0,03836 W/mK (density _{mean} 9,2 kg/m ³) 0,039
2.4.9	Compressive strength at 10 % deformation, EN 826	11,2 kPa
2.4.10	Tensile strength parallel to faces, EN 1608	11,3 kPa
2.4.11	Tensile strength perpendicular to faces, EN 1607	11,5, kPa
2.4.12	Dimensional stability (length/width/thickness) +70 °C, 90 %RH, 48 h , EN 1604 +23 °C, 75 % RH, 48 h, EN 1603 - 20 °C, 48 h, EN 1604	+ 0,27/+ 0,20/+ 0,97 % No changes of flatness were found - 0,02/- 0,01/- 0,01 %
Related aspects of serviceability		

*In addition of the specific clauses relating to dangerous substances contained in this European Technical Approval, there may be other requirements applicable to the products falling within its scope (e.g. transposed European legislation and national laws, regulations and administrative provisions). In order to meet the provisions of the Construction Products directive, these requirements need also to be compiled with, when and where they apply.

** Calculated from the λ_{90/90, dry at 10 °C}

3. Evaluation and attestation of conformity and CE marking

3.1 System of attestation of conformity

According to the decision 99/91/EC of 25.01.1999 of the European Commission the system 3 of attestation of conformity applies, since there is no improvements of the reaction to fire classification in the production process.

This system of attestation of conformity is defined as follows:

System 3: declaration of conformity of the product by the manufacturer on the basis of:

(a) Tasks for the manufacturer:

(1) Factory production control,

(2) Testing of samples taken at the factory in accordance with the prescribed test

plan

(b) Tasks for the notified body:

(3) Initial type testing of the product

3.2 Tasks for the manufacturer

3.2.1 Factory production control

The manufacturer continues to operate a factory production control system. Quality control checks are made on incoming materials, and at regular stages throughout the production sequence to ensure the quality and fitness for use of the product.

VTT Expert Services Ltd maintains a file describing the tasks and tests imposed on ETA holder. The file includes information of the main raw materials and "Control plan" which include the type and frequency of the manufacturers factory production control agreed between approval holder and VTT Expert Services Ltd:

The results of factory production control shall be recorded and evaluated in accordance with the provisions of the "Control plan".

3.2.2 Initial type testing of the product

For initial type testing the results of the tests performed as part of the assessment for this European Technical Approval shall be used unless there are changes in the production line or plant. In such cases the necessary type testing has to be agreed between VTT Expert Services Ltd and the manufacturer.

3.3 CE-marking

The CE-marking shall be affixed on the each packaging or on the delivery tickets put into the packages. The symbol "CE" shall be accompanied by the following additional information:

- Name of the product: Commercial trade name as indicated in this ETA
- Name and address of the ETA holder (legal entity responsible for the manufacture)
- The last two digits of the year in which the CE marking was affixed
- The number of the European Technical Approval, ETA - 13/0613
- Declared and at least most essential properties according to the following:
 - Thermal conductivity, $\lambda_{90/90}$
 - Compression strength/stress
 - Tensile strength parallel to faces
 - Dimensional stability
 - Water absorption
 - Water vapour permeability
 - Corrosion developing capacity

4. Assumptions under which the fitness of the product for the intended use was favourably assessed

4.1 Manufacturing

Manufacturing of the soft foam thermal insulation is based on the defined production method, use of defined raw materials and tolerances. If changes take place manufacturer is responsible to clarify if the change has influence on the properties of the product tested according to the provisions of the CUAP.

The European technical approval is issued for the product on the basis of agreed data/information, deposited with VTT Expert Services Ltd, which identifies the product that has been assessed and judged. Changes to the product or production process, which could result in this deposited data/information being incorrect, should be notified to VTT Expert Services Ltd before the changes are introduced. VTT Expert Services Ltd will decide whether or not such changes affect the approval and consequently the validity of the CE marking on the basis of the approval and if so whether further assessment or alterations to the approval shall be necessary.

4.2 Installation

The thermal insulation is installed on to the building according to the instructions of the manufacturer. The suitability of the insulation to the planned purpose shall be evaluated taking into account what has been said in chapter 1.2.

5. Indications to the manufacturer

5.1 Packaging transport and storage

The insulation products are transported to the building site in barrels. The products components shall be stored at temperatures between +10 - +30 °C before the installation.

5.2 Use, maintenance and repair

The thermal insulation shall work adequately when the construction where it is installed according to the instructions of the manufacturer is maintained and repaired so that the provisions of use given in chapter 1.2 of this ETA are fulfilled.

On behalf of VTT Expert Services Ltd

Espoo June 30, 2013



Liisa Rautiainen
Assessment Manager



Pertti Jokinen
Assessor