

TECHNICAL DATA SHEET

Heatlok® HFO High Lift is a two component, closed cell, spray applied, rigid polyurethane foam system. This product uses recycled plastic materials, rapidly renewable soy oils, and the blowing agent has zero ozone depleting potential. Heatlok HFO High Lift complies with the intent of the International Code Council's residential and commercial building codes and is commonly used as a thermal insulation, air barrier, vapor retarder and water resistive barrier in above grade, below grade, interior and exterior applications.

PHYSICAL PROPERTIES			
ASTM D 1622	Core Density	2.0 – 2.4 lb/ft ³	32.0 – 38.4 kg/m ³
ASTM C 518	Aged Thermal Resistance	1" = 6.3 ft ² h°F/BTU 3.5" = 26 ft ² h°F/BTU	1" = 1.10 Km ² /W 3.5" = 4.57 Km ² /W
ASTM E 283	Air Leakage @ 75 Pa @ 1"	< 0.02 L/sm ²	
ASTM E 2178	Air Permeance @ 75 Pa @ 1"	< 0.02 L/sm ²	
ASTM E 96	Water Vapor Permeance Qualifies as a Class III vapor barrier per IBC Section 202	1.56 perms	89.25 ng/Pa•s•m ²
ASTM D 2842	Water Absorption (volume)	0.87%	
ASTM D 1621	Compressive Strength	34.8 psi	240 kPa
ASTM D 1623	Tensile Strength	101.3 psi	698 kPa
ASTM D 2126	Dimensional Stability @ 158°F (70°C) 97% R.H. (168 hours)	11.4% (% volume change)	
VOC Emissions	UL Environment (Greenguard Gold)	Meets Criteria	
ASTM C 1338	Fungi Resistance	No fungal growth	
ASTM D 2856	Closed Cell Content	91%	

FIRE TEST RESULTS		
ASTM E 84	Surface Burning Characteristics, 4" thick Flame Spread Index Smoke Developed	Class I 10 - 15 350 - 400
AC 377 Appendix X	Ignition Barrier - Compliant with 2009, 2012 & 2015 IBC and IRC, and ICC-ES AC-377 Appendix X, for use in attics and crawl spaces without a prescriptive ignition barrier or intumescent coating.	Pass
NFPA 286	Thermal Barrier - Compliant with the 2009, 2012 & 2015 IBC and IRC, as an interior finish without a 15 minute thermal barrier when coated with DC-315 at 18 mils wet film thickness, 12 mils dry film thickness.	Pass
ASTM D 1929	Ignition Properties (spontaneous ignition temperature)	766°F (408°C)

REACTIVITY PROFILE			
Cream Time	Gel Time	Tack Free Time	End of Rise
0 - 1 seconds	2 seconds	3 - 4 seconds	3 - 4 seconds

LIQUID COMPONENT PROPERTIES*		
PROPERTY	A-PMDI ISOCYANATE	HEATLOK HFO HIGH LIFT RESIN
Color	Brown	Blue
Viscosity @ 77°F (25°C)	180 – 220 cps	500 – 800 cps
Specific Gravity	1.24	1.17 – 1.21
Shelf Life of unopened drum properly stored	12 months	6 months
Storage Temperature	50 – 100°F (10 – 38°C)	59 – 77°F (15 – 25°C)
Mixing Ratio (volume)	1:1	1:1

*See SDS for more information.

RECOMMENDED PROCESSING CONDITIONS*		
Initial Primary Heater Setpoint Temperature	105 – 115°F	41 – 46°C
Initial Hose Heat Setpoint Temperature	105 – 115°F	41 – 46°C
Initial Processing Setpoint Pressure	1200 – 1400 psi	8274 – 9653 kPa
Substrate & Ambient Temperature	Summer > 50°F Winter > 15°F	Summer > 10°C Winter > -9°C
Moisture Content of Substrate	≤19%	≤19%
Moisture Content of Concrete	Concrete must be cured, dry and free of dust and form release agents.	

*Foam application temperatures and pressures can vary widely depending on temperature, humidity, elevation, substrate, equipment and other factors. While processing, the applicator must continuously observe the characteristics of the sprayed foam and adjust processing temperatures and pressures to maintain proper cell structure, adhesion, cohesion and general foam quality. It is the sole responsibility of the applicator to process and apply Heatlok HFO High Lift within specification.

General Requirements: Equipment must be capable of delivering the proper ratio (1:1 by volume) of polymeric isocyanate (PMDI) and polyol blend at adequate temperatures and spray pressures. Substrate must be at least 5 degrees above dew point, with best processing results when ambient humidity is below 80%. Substrate must also be free of moisture (dew or frost), grease, oil, solvents and other materials that would adversely affect adhesion of the polyurethane foam. Applicators should limit the application of this product to no more than a thickness of 6.5” (165mm) per pass (after expansion) to avoid fire hazards (including spontaneous combustion) resulting from excessive heat generation. If subsequent passes are needed, applicators should wait until the core temperature of the foam has dropped below 100°F to allow any reaction heat to dissipate from the prior applications before attempting to reapply the product.

Heatlok HFO High Lift must be separated from the interior of the building by an approved thermal barrier or an approved finish material equivalent to a thermal barrier in accordance with applicable codes. Heatlok HFO High Lift must be sprayed at a minimum thickness of 1” per pass. This product must not be used when the continuous service temperature of the substrate or foam is below -60°F (-51°C) or above 180°F (82°C). Heatlok HFO High Lift should not be used to cover flexible ductwork.

Disclaimer: The information herein is to assist customers in determining whether our products are suitable for their applications. We request that customers inspect and test our products before use and satisfy themselves as to contents and suitability. Nothing herein shall constitute a warranty, expressed or implied, including any warranty of merchantability or fitness, nor is protection from any law or patent inferred. All patent rights are reserved. The foam product is combustible and must be protected in accordance with applicable codes. Protect from direct flame and spark contact, around hot work for example. The exclusive remedy for all proven claims is replacement of our materials.

